

## MaxiTorch APP Premium Mineral



### Product Overview

Easy-Trim MaxiTorch APP Premium Mineral is an APP polymer modified bituminous membrane, with non-woven polyester core, giving it flexibility, strength and puncture resistance. Designed for use on both new and refurbishment flat roofing projects. Maxi Torch APP Premium Mineral is manufactured with a mineral finish on the upper surface, which ensures a desired finish and also provides protection against UV degradation, along with a PE film backing.

#### Benefits

- Ideal for new and refurbishment projects
- High bond strength

### Application

MaxiTorch APP Premium Mineral is suitable for use as a capsheet over an underlay, in a bitumen built up bituminous roofing system, or as a single layer capsheet over compatible materials.

The installation of all torch on bituminous systems, must be carried out by experienced roofers, and in accordance with BS8217:2005, Reinforced bitumen membranes for roofing. Code of practice and in accordance with the manufacturers guidelines. Care must be taken, to ensure that recommended good practices for the installation of torch on membranes are diligently followed during the installation process.

### Technical Characteristics

Characteristics	Test Method	Unit	Nominal Values	Tolerances
Visible defects	EN 1850-1	visible	Without defects	Not relevant
Length	EN 1848-1	m	8,000 -1%	MLV
Width	EN 1848-1	m	1,000 -1%	MLV
Straightness	EN 1848-1	mm	20 mm x 10 m	Pass
Mass per unit area	EN 1849-1	Kg/mq	5 ± 10%	Not relevant
Watertightness (A)	EN 1928	kPa	60	MLV
External fire performance	EN 13501-5	B roof	F Roof	Not relevant
Reaction to fire	EN 13501-1	Class	F	Pass
Tensile Strength Longitudinal / Transversal	EN 12311-1	N/50 mm	600 / 500	± 20%
Elongation at break Longitudinal / Transversal	EN 12311-1	%	45 / 45	- 15 absolut
Resistance to impact	EN 12691	mm	700	MLV
Resistance to static loading Method A	EN 12730	Kg	10	MLV
Resistance to tearing (nail shank) E	N 12310-1	N	180 / 180	- 30%
Dimensional stability Longitudinal / Transversal	EN 1107-1 met. A	%	± 0,3 %	MLV
Flexibility at low temperature	EN 1109	°C	-5	MLV
Flow resistance at elevated temperature	EN 1110	°C	110	MLV
Flow resistance at elevated temperature after artificial ageing	EN 1296 / EN 1110	°C	110 -10	Not relevant
Adhesion of granules	EN 12039	%	Max 30 %	MDV

Tel: +44 (0) 845 034 6008

e: enquiries@easy-trim.co.uk

f: +44 (0) 845 034 6010

Unit 12B Metcalf Drive  
 Altham Industrial Estate | Altham  
 Lancashire | BB5 5TU | England

w: www.easy-trim.co.uk

find us:



## MaxiTorch APP Premium Mineral

### Storage

All our roofing felts are delivered on appropriate pallets, stood on end. Care must be taken to ensure the material is stood on end on flat level surfaces at all times, before its installed.

### Disclaimer

The information relates only to this specified material and may not be valid for such materials used in combinations with other materials and processes. This information is, to the best of the Company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty, guarantee or representation is made to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability of the information on the material for their own particular use.

Tel: +44 (0) 845 034 6008

e: [enquiries@easy-trim.co.uk](mailto:enquiries@easy-trim.co.uk)

f: +44 (0) 845 034 6010

Unit 12B Metcalf Drive  
Altham Industrial Estate | Altham  
Lancashire | BB5 5TU | England

w: [www.easy-trim.co.uk](http://www.easy-trim.co.uk)

find us:

